

Supporting Information

for

Synthesis of guanidinium–sulfonimide ion pairs: towards novel ionic liquid crystals

Martin Butschies, Manuel M. Neidhardt, Markus Mansueto, Sabine Laschat*, Stefan Tussetschläger

Address: Institut für Organische Chemie, Universität Stuttgart, Pfaffenwalring 55, 70569 Stuttgart, Germany

Email: Sabine Laschat - sabine.laschat@oc.uni-stuttgart.de

*Corresponding author

DSC traces of compounds 2a,b, 3a and X-ray data of compound 3b

DSC traces of compounds (2a,b) and (3a):




Figure S1: DSC trace of compound 3a (heating/cooling rate 10 K min⁻¹).




Figure S2: DSC trace of compound 2a (heating/cooling rate 10 K min⁻¹).




Figure S3: DSC trace of compound **2b** (heating/cooling rate 10 K min^{-1}).

X-ray data of compound (3b):

Table S1: Temperature-dependent layer spacing of compound **3b**.

Temperature	Layer spacing
$T/[\text{°C}]$	$d_{001}/[\text{Å}]$
75.2	34.19
59.5	34.16
43.8	35.38
WAXS 59.5	4.74 (halo)

Table S2: Water content of selected compounds.

Comp.	Sample weight [mg]	Weight of CH ₂ Cl ₂ [mg]	Concentration (sample weight/ weight of CH ₂ Cl ₂)	Weight of the solution in [mg]	Detected mass of H ₂ O in [μg]	% H ₂ O
CH ₂ Cl ₂	1369.8	–	–	1369.8	32.0 ^(a)	2.34·10 ⁻³
CH ₂ Cl ₂	1098.9	–	–	1098.9	26.6 ^(a)	2.42·10 ⁻³
7-I	51.25	2988.71	1.69·10 ⁻²	932.7	42.2	0.13
2b	47.38	2076.88	1.56·10 ⁻²	1656.0	136.8	0.38
3a	41.45	2606.73	1.37·10 ⁻²	2012.4	145.3	0.36

(a) Ø = 23.8 μg H₂O in 1 g abs. CH₂Cl₂